

## RESOLUTION OIV-OENO 681-2022

### POWDERED CELLULOSE

THE GENERAL ASSEMBLY,

CONSIDERING Article 2, paragraph 2 iv of the Agreement of 3 April 2001 establishing the International Organisation of Vine and Wine,

CONSIDERING that microfibre-composed celluloses of recognised food-grade quality have been in existence for some years now, and that these could substitute microcrystalline cellulose at a lower cost, it has been proposed that the TECHNO Group make a decision on the possible use of these food celluloses or powder celluloses. This practice has been adopted, which is reflected in the addition of food cellulose to file 2.3.2 of the *Code* as a fermentation activator (OIV-OENO 633-2019).

CONSIDERING the work of the “Specifications of Oenological Products” Expert Group, DECIDES, at the proposal of “Oenology” Commission II, to add the following monograph to Chapter I of the *International Oenological Codex*:

#### POWDERED CELLULOSE

(C<sub>12</sub>H<sub>20</sub>O<sub>10</sub>)<sub>n</sub>

INS No.: 460 (ii)

CAS No.: 9004-34-6

### 1. Object, origin and scope of application

Powdered cellulose is cellulose of food-grade quality. Cellulose is a linear glucose homopolymer composed of glucopyranose units linked by  $\alpha$ -1,4-glycosidic bonds; its degree of polymerisation (DP) is dependent on the origin of the cellulosic material.

Powdered cellulose is a non-modified, purified cellulose, obtained by the mechanical disintegration of alpha-cellulose procured in pulp form from fibrous plant material.

Powdered cellulose plays a “support” role in clarified fermentation media; it allows for improved “degassing” of carbon dioxide at the start of alcoholic fermentation and thus shortens the latency phase. It increases the fermentability of must.

### 2. Labelling

The following should be mentioned on the label:

- the identification of the cellulose and its use in food,
- the concentration of the product, including in the case of a mixture,
- safety and storage conditions
- the batch no.,
- the expiry date.

### **3. Characteristics**

Powdered cellulose comes in the form of flakes or very fine fibres, and is whitish in colour, odourless and flavourless.

### **4. Test limits and methods**

#### **4.1. Identification**

Place approx. 10 mg powdered cellulose on a watch glass and disperse into 2 mL iodinated zinc chloride solution (R). The solution will turn a blue-purple colour.

#### **4.2. Solubility**

Powdered cellulose is insoluble in water, ethanol, ether and diluted acids, and slightly soluble in sodium hydroxide solution.

#### **4.3. Purity**

The powdered cellulose content should not be less than 92%.

#### **4.4. Size of fine particles**

The size of fine particles should not be less than 5  $\mu\text{m}$ ; the number of particles smaller than 5  $\mu\text{m}$  should not exceed 10%.

#### **4.5. pH**

Mix approx. 10 g dry cellulose in 90 mL water free of carbon dioxide for 60 min. Centrifuge. The pH of the supernatant liquid should be between 5.0 and 7.5.

#### **4.6. Water-soluble substances**

Mix around 6 g of sample, dried beforehand, with 90 mL water that has recently been boiled then cooled. Leave to rest for 10 min. Filter using a membrane with porosity of 3  $\mu\text{m}$ , throw away the first 10 mL of filtrate and pass the filtrate through the same filter a second time if necessary to obtain a clear filtrate. Evaporate a 15-mL portion of filtrate to dryness in a tared evaporating dish over a water bath, and dry to 105 °C for 1 h. Weigh the dish containing the dry residue. Less than 15 mg of residue should be obtained.

#### **4.7. Detection of starch**

Add 90 mL demineralised water (R) to 10 g powdered cellulose and boil for 5 min. Filter while hot with a 25-  $\mu\text{m}$  membrane filter. Cool and add 0.1 mL 0.05 M iodine solution to the filtrate. No blue colouration should appear. With very fine grains, a light blue colour may be observed after the addition of the iodine solution but will disappear after 30 minutes.

#### **4.8. Loss on drying**

Place 1 g powdered cellulose in a tared dish in an oven at 100-105 °C for 3 hours. The loss on drying should not exceed 7.0%.

#### **4.9. Ashes**

Incinerate the residue obtained in point 4.8 at  $800 \pm 25$  °C for 4 hours. The weight of the ashes should not be greater than 0.3%.

All of the limits set below relate to dry products.

### **5. Preparation of the test solution**

After weighing, dissolve the ashes in 2 mL concentrated hydrochloric acid (R) and 10 mL water (R). Heat to activate dissolution and make up to 50 mL with water.

#### **5.1. Iron**

Determine the iron content of the solution prepared for testing purposes (5) by atomic absorption spectrophotometry according to the method described in Chapter II. The iron content should be less than or equal to 10 mg/kg.

## 5.2. Lead

Determine the lead content of the solution prepared for testing purposes (5) according to the method described in Chapter II. The lead content should be less than 2 mg/kg.

## 5.3. Mercury

Determine the mercury content of the solution prepared for testing purposes (5) according to the method described in Chapter II. The mercury content should be less than 1 mg/kg.

## 5.4. Cadmium

Determine the cadmium content of the solution prepared for testing purposes (5) according to the method described in Chapter II. The cadmium content should be less than 1 mg/kg.

## 5.5. Arsenic

Determine the arsenic content of the solution prepared for testing purposes (5) according to the method described in Chapter II. The arsenic content should be less than 1 mg/kg.

## 6. Storage

Powdered cellulose should be stored in a well-ventilated place in airtight packaging, away from any volatile substances that it could adsorb.